

## Mill test

HEAT NO.			CHEMICAL ANALYSIS, %										
			C	Mn	P	S	SI	AL	CB	V	CU	NI	CR
764622	C.E.	.11	.05	.22	.006	.010	.01	.036	.001	.001	.140	.040	.070
764701	C.E.	.11	.06	.18	.003	.005	.01	.031	.001	.001	.070	.020	.080

## Description

Tube : 2.375", RD 057, GALVALUME, AZM120  
78" / 90" / 102"

## Specification

ASTM A513 AWCR TYPE 2 19



**Mathieu Cardinal, B.A.A.**

Directeur General / General Manager  
Clôtures Directes Inc.

238 Boul Industriel, Châteauguay, Québec, J6J 4Z2

Téléphone : 450-692-1221 poste 225

Télécopieur : 450-692-1644

<http://www.cloturesdirectes.ca/fr/>